

Unique products by design & innovation

Colour Range

July 2016

STANDARD COLOUR RANGE



Pearl White



Woodland Grey




Ultra Silver



Monument




Classic Cream



Surfmist



Paperbark



Black

CONTEMPORARY COLOUR RANGE



Clear Anodised



Deep Ocean




Wallaby



Windspray



Manor Red



Dune




Evening Haze



Ironstone



Pale Eucalypt



Shale Grey



White Birch



Jasper

EFFECTA COLOUR RANGE




Snow Gum



Honey Gum



Cedar



Mahogany

COLOUR SELECTOR

Please obtain a comprehensive quote prior to placing your order as delivery time & costs will vary depending on your choice. Colours shown on this selector are intended as a guide only and are as close as modern printing processes allow. Westal recommends the viewing of colour swatch or aluminium sample before ordering. COLOURBOND® and ® and ™ colour names are registered trademarks of BlueScope Steel Limited.

Phone: 02 6391 4800

www.westal.com.au

A: 15 Astill Drive Narrambla Business Park Orange NSW 2800 - **F:** 02 6360 1182 - **E:** sales@westal.com.au

Maintenance of Powder Coated & Anodised Aluminium

Cleaning is necessary if the fine finish of powder coated and anodised aluminium is to be preserved. Deterioration of the coating occurs mainly as a result of grime deposition and attack by contaminated moisture which in a coastal environment contains salt and sulphur compounds. Deposited grime and contamination absorbs moisture like a sponge and holds it against the powder coated and anodized surfaces. This permits the attack to proceed thereby damaging the coating which cannot be restored.

Frequency Of Cleaning:

Cleaning required is dependent on the severity of the environment

Rural/Suburban Environments

The maximum period between cleaning should never be more than six (6) months.

Coastal/Industrial Environments

More frequent cleaning is necessary and the maximum period between cleaning should never be more than three (3) months. Under the worst conditions involving heavy grime deposition and atmospheric pollution (e.g. sulphur compounds or salts) more frequent cleaning is advisable e.g. monthly, if deterioration of the coating is to be prevented.

The cleaning of powder coated and anodised material should be performed using hand-cleaning and rinsing techniques. This should be achieved by using small amounts of clean water and recommended cleaning products. Do not under any circumstances use an abrasive type of cleaning agent as this will severely damage the surface of the material. Hosing must be avoided under all circumstances. Dry preferably with a chamois, or alternatively, a soft cloth.

The cleaning of the product should be performed at a time that will allow the aluminium to dry quickly, preferably early in the morning.

We recommend the use of the following automotive cleaning products.

Kitten "Glo-Wash"

Turtle Wax "Zip Wash"

RE-PO "Superwash"

Should the above products give less than the desired results, the following car polishes can be used as per the manufacturer's recommendation.

Turtle Wax "Car Polish"

RE-PO "Car Cream Polish"

NOTE: Use only the above mentioned cleaning products. Do not use alternative products by the same or other (manufacturers) without written authorization from Westal Windows.